

Z735

NBR 60 black

Rev. 03

General Application Temperature Range

From -40°C
To +110°C

General Environmental Application

Mineral Oils
Gas
UV Rays

Curing System

Suplhur

Compliances

Note

Disclaimer

Tests performed on test slabs. Temperatures, applications, and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

PHYSICAL AND MECHANICAL PROPRIETIES

Property	Test STD	Unit	Value
Density	ISO 2781 A	g/cm ³	1.25 ± 0.03
Hardness	ASTM D2240	Shore A	60 ± 5
Tensile Strength	ISO 37	N/mm ²	>14
Elongation	ISO 37	%	>625

LOW TEMPERATURE RESISTANCE

Property	Test STD	Unit	Value
TR10	ISO 2921	°C	<-25

COMPRESSION SET TESTS

Parameters	TEST STD	Unit	Value
24h @ 70°C	ISO 815-1 A	%	<13
72h @ -20°C	ISO 815-1 A	%	<19

AGEING PROPERTIES

Heat Aging – 168h @ 100°C

Standard: ISO 188

Properties	Unit	Value
Hardness	Shore A	+5.0
Tensile Strength	%	-7.0
Elongation	%	-8.0
Volume	%	
Weigth	%	

IRM OIL 902 – 168h @ 60°C

Standard: ISO 1817

Properties	Unit	Value
Hardness	Shore A	-2.0
Tensile Strength	%	
Elongation	%	
Volume	%	-1.0
Weigth	%	-1.0

Pentane – 70h @ 23°C

Standard: ISO 1817

Properties	Unit	Value
Hardness	Shore A	
Tensile Strength	%	
Elongation	%	
Volume	%	
Weigth	%	+2.0

IRM OIL 903 – 70h @ 23°C

Standard:

Properties	Unit	Value
Hardness	Shore A	-5.0
Tensile Strength	%	
Elongation	%	
Volume	%	+4.0
Weigth	%	+2.0

